



**DIVERSIFIED**  
**TESTING LABORATORIES, INC.**  
 WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
 P.O. BOX 4004  
 BURLINGTON, NORTH CAROLINA 27215  
 PHONE (336) 227-7710 • FAX (336) 227-1175  
 www.diversifiedtestinglabs.com

August 17, 2020

Ms. Cheri Kepp  
 FLAME SAFE  
 2653 Warfield Avenue  
 Fort Worth, TX 76106

Reference: Laboratory Test Report  
 Lab Identification No. 42311  
 Invoice No. 73556

Dear Ms. Kepp:

One (1) sample, identified as **PINK ARTIFICIAL SILK HANGING VINE TREATED WITH FLAME SAFE FIRE POLY FPCC FIRE RETARDANT WITH A COVERAGE RATE OF 300 SQUARE FEET PER GALLON**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u>	
	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	2.41
2	0.0	10.43
3	0.0	9.79
4	0.0	11.67
5	0.0	11.72
6	0.0	7.08
7	0.0	22.41
8	0.0	19.74
9	0.0	28.52
<u>10</u>	<u>0.0</u>	<u>19.36</u>
AVG	0.0	14.31

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr



OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. SAMPLES NOT DESTROYED TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.